



## UTR Angles and Channels

### Electrical Insulating Structural Products

- Grade UTR Pultrusions
- Dimensions are in inches
- All parts are available in standard lengths of 120" except 2261 and 2890

Channel				
Part No.	Width	Leg	Thickness	Inside Radius
2875	2	$\frac{9}{16}$	$\frac{1}{8}$	$\frac{1}{8}$
2617	2	$\frac{13}{16}$	$\frac{1}{8}$	$\frac{5}{32}$
1144	2	1	$\frac{1}{4}$	$\frac{1}{8}$
2261	$2\frac{3}{16}$	$\frac{3}{4}$	$\frac{1}{16}$	$\frac{1}{8}$
2212	$2\frac{5}{16}$	$\frac{3}{4}$	$\frac{1}{8}$	$\frac{1}{8}$
1177	$2\frac{9}{16}$	$1\frac{7}{32}$	$\frac{1}{8}$	$\frac{3}{16}$
1166	3	$\frac{7}{8}$	$\frac{1}{4}$	$\frac{1}{4}$
2888	3	$1\frac{1}{2}$	$\frac{1}{4}$	$\frac{1}{4}$
1939	$3\frac{9}{16}$	$2\frac{9}{16}$	$\frac{3}{16}$	$\frac{3}{16}$
1791	$3\frac{19}{32}$	$1\frac{1}{8}$	$\frac{1}{8}$	$\frac{1}{8}$
1155	4	$1\frac{1}{8}$	$\frac{1}{4}$	$\frac{1}{4}$
2242	4	$1\frac{3}{8}$	$\frac{3}{16}$	$\frac{5}{32}$
2872	$4\frac{1}{2}$	$2\frac{1}{2}$	$\frac{1}{8}$	
2874	$4\frac{1}{2}$	$2\frac{1}{2}$	$\frac{1}{4}$	$\frac{1}{8}$
1940	$4\frac{9}{16}$	$2\frac{9}{16}$	$\frac{9}{32}$	$\frac{1}{4}$
1788	$4\frac{3}{4}$	$1\frac{5}{8}$	$\frac{3}{16}$	$\frac{3}{16}$
2825	$5\frac{1}{2}$	$1\frac{1}{4}$	$\frac{5}{32}$	$\frac{3}{16}$
2288	$6\frac{3}{8}$	2	$\frac{9}{32}$	$\frac{3}{32}$
1844	$8\frac{1}{2}$	$2\frac{11}{16}$	$\frac{3}{16}$	$\frac{7}{32}$
1936	$9\frac{21}{32}$	$1\frac{5}{8}$	$\frac{1}{8}$	$\frac{3}{32}$
2250	$11\frac{9}{32}$	$1\frac{5}{8}$	$\frac{3}{8}$	$\frac{3}{32}$
2120	$11\frac{1}{2}$	$1\frac{7}{16}$	$\frac{5}{32}$	$\frac{1}{8}$

Hat Shaped Channel				
Part No.	Width	Leg	Thickness	Inside Radius
1161	$4\frac{19}{32}$	$\frac{7}{8}$	$\frac{1}{8}$	$\frac{1}{4}$
2091	5	$1\frac{3}{8}$	$\frac{1}{8}$	$\frac{5}{32}$
1272	$9\frac{9}{16}$	$2\frac{3}{8}$	$\frac{3}{16}$	$\frac{1}{4}$


Equal Leg Angles				
Part No.	Width	Leg	Thickness	Inside Radius
2878	1	1	$\frac{1}{8}$	$\frac{1}{8}$
2889	$1\frac{1}{4}$	$1\frac{1}{4}$	$\frac{1}{8}$	$\frac{1}{8}$
2879	$1\frac{1}{4}$	$1\frac{1}{4}$	$\frac{3}{16}$	$\frac{1}{4}$
2880	$1\frac{1}{2}$	$1\frac{1}{2}$	$\frac{1}{8}$	$\frac{1}{8}$
2881	$1\frac{1}{2}$	$1\frac{1}{2}$	$\frac{3}{16}$	$\frac{1}{4}$
2882	$1\frac{1}{2}$	$1\frac{1}{2}$	$\frac{1}{4}$	$\frac{3}{8}$
2883	2	2	$\frac{3}{16}$	$\frac{1}{4}$
2884	2	2	$\frac{1}{4}$	$\frac{3}{8}$
2885	3	3	$\frac{1}{4}$	$\frac{3}{8}$
2886	3	3	$\frac{3}{8}$	$\frac{3}{8}$

Unequal Leg Angles				
Part No.	Width	Leg	Thickness	Inside Radius
1134*	$1\frac{3}{4}$	2	$\frac{3}{8}$	$\frac{3}{8}$
2891	$2\frac{1}{4}$	3	$\frac{1}{2}$	$\frac{1}{2}$
2876	$2\frac{1}{4}$	$1\frac{1}{2}$	$\frac{3}{16}$	$\frac{1}{8}$
1133	$2\frac{1}{2}$	$1\frac{1}{4}$	$\frac{3}{16}$	$\frac{1}{4}$
2877	$2\frac{3}{4}$	2	$\frac{1}{4}$	$\frac{1}{8}$
2890	6	3	$\frac{1}{2}$	$\frac{1}{2}$

\* Also sold in 7' lengths

Terminal Strips			
Part No.	Width	Leg	Thickness
2700	$\frac{3}{8}$	$\frac{1}{8}$	$1\frac{1}{4}$
2710	$\frac{7}{16}$	$\frac{1}{4}$	$1\frac{1}{2}$
2720	-	$\frac{1}{2}$	2

Rectangular Tube			
Part No.	Width	Leg	Thickness
F822024	$1\frac{1}{2}$	$1\frac{1}{2}$	$\frac{1}{8}$
F822432	2	2	$\frac{1}{4}$



## UTR Angles and Channels

	Unit	ASTM/UL Test	Typical Values <sup>1</sup>	
<b>General Information</b>				
Color, Standard	–	–	Red	
NEMA Grade	–	–	GPO-3	
UL Recognition File Number	–	–	E 23525	
<b>Mechanical Properties</b>				
Tensile Strength	Psi	D 638	15,000	
Tensile Modulus	Psi x 10 <sup>6</sup>	D 638	1.7	
Flexural Strength	Psi	D 790	25,000	
Flexural Strength at 130° C	Psi	D 790	13,000	
Flexural Modulus	Psi x 10 <sup>6</sup>	D 790	1.2	
Compressive Strength – flatwise	Psi	D 695	42,000	
Compressive Strength – edgewise	Psi	D 695	20,000	
Shear Strength	Psi	D 732	14,500	
IZOD Impact Strength (notched)	Ft.lb./in.	D 256	9.6	
Water Absorption	% by wt.	D 570	0.3	
Barcol Harness	–	D 2583	50	
Specific Gravity	–	D 792	1.8	
<b>Electrical Properties</b>				
Electric Strength – perpendicular S/T in air <sup>2</sup>	Vpm	D 149	200	
Electric Strength-parallel	kV	D 149	45	
Arc Resistance	Seconds	D 495	185	
Inclined Plane Track Resistance	Minutes	D 2303	500+	
<b>Flame &amp; Smoke Characteristics</b>				
UL Subject 94	–	UL 94	V0	
Specific Optical Density of Smoke		ASTM E662		
			Non-Flaming	Flaming
Ds @ 4.0 min.(Average)			0.3	10.7
Dm(corr) (Average)			3.1	128.4
<b>Thermal Properties</b>				
Coefficient of Thermal Expansion	in/in/°C x 10 <sup>-5</sup>	D 696	2.0	
Thermal Conductivity	BTU/hr/Ft <sup>2</sup> /in/°F	C 177	1.9	
UL Temperature Index				
Electrical	°C	UL746B	130	
Mechanical	°C	UL746B	160	
<b>Dimension Tolerances</b>				
Thickness				
Up to .125 in.	in.	–	±.015	
.125 in. – .250 in.	in.	–	±.020	
over .250 in.	in.	–	±.025	
Angularity of Legs	Degrees	–	±3	
Cut Length	in.	–	+0.5", -0"	

1 These products are manufactured in a variety of sizes, shapes and thicknesses.  
Data shown is a composite of all products.

2 Value for 1/8 in. thickness. Electric strength in volts per mill decreases as composite thickness increases.

Röchling Glastic Composites  
 4321 Glenridge Road  
 Cleveland, OH 44121 USA  
 Tel: 216-486-0100  
 Fax: 216-486-1091  
[www.glastic.com](http://www.glastic.com)

All of the information, suggestions, and recommendations pertaining to the properties and uses of the Röchling Glastic Composites products described herein are based upon tests and data believed to be accurate; however, the final determination regarding the suitability of any material described herein for the use contemplated, the manner of such use, and whether the use infringes any patents is the sole responsibility of the user. THERE IS NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Under no circumstances shall we be liable for incidental or consequential loss or damage.

Glastic® is a registered trademark of Röchling Glastic Composites. UL® is a registered trademark of Underwriters Laboratories, Inc.

©2012 Röchling Glastic Composites. All Rights Reserved. Printed in USA.