




DATA SHEET


RDEB

ROD, EBONITE UNPOLISHED
CLASS A (105°C)



ROD

	UNITE	ROD	PLATE
Specific Gravity	%	1.16	1.14
Absorption	Mg/100cm ²	0.25~0.3	0.2~0.3
Heat resistance for appearance	-	unchange	unchange
Heat resistance for demention	-	unchange	unchange
Heatproof	mm	2~3	2~3
Tencil Strength	Kg/mm ²	6~7	6~7
Spread	%	4~6	4~6
Compression Strength	Kg/mm ²	8~10	8~10
Bend Strength	Kg/mm ²	10~11	10~11
Aceton	%	4.3~4.7	4.3~4.7
Insulation Distruction Strength	Kv/mm	27~29	27~29
Own resistance for capacity	Ωcm	10 ¹³	10 ¹⁵
Own resistance for surface	Ω	10 ¹³	10 ¹⁵
Isolater sulphur	%	0.3~0.9	0.3~0.9
Soften Point	°C	80	80



Temperature Index