



Grade FHT

Flexible, High-Temperature Laminate

- Highly Flexible
- Excellent Dielectric Strength
- High Heat Resistance
- Ideal For Dry-Type Transformers
- Easily Fabricated
- Asbestos-Free

Grade FHT (Flexible High Temperature) Laminate provides numerous high-performance features and benefits, such as high flexibility and excellent dielectric strength at elevated temperatures. It also exhibits the highest UL® temperature index in the industry for a flexible glass-reinforced polyester in 1/32 inch and 1/16 inch thicknesses:

- 1/32" – 190° C Electrical
- 1/16" – 200° C Electrical
- 1/32" – 190° C Mechanical
- 1/16" – 200° C Mechanical

With its high resistance to heat, FHT Laminate offers a cost-effective alternative to aramid paper in 220°C insulation systems. Typical applications include layer and core insulation for dry-type transformers.

Grade SG-200

High-Strength & High-Temperature Laminate

- Extremely Strong
- Excellent Retention Of Properties At Elevated Temperatures
- Ideal For High Temperature Applications
- Easily Fabricated
- Asbestos-Free

Grade SG-200 High-Strength & High-Temperature Laminate offers the same high-performance features and benefits as FHT Laminate. In addition, SG-200 offers much higher mechanical strengths than FHT with temperature ratings of up to 210° C.

Because of its capabilities, SG-200 is ideal for a wide variety of product applications requiring high-temperature NEMA GPO-1 products. Grade SG-200 is also a superior replacement material for epoxy-bonded mica in layer insulation applications. SG-200 has a UL Temperature Index of 210° C Electrical and 210° C Mechanical.

Grade SG-200 is available in thicknesses of 1/32" to 2 1/2". Special sheet sizes of 64" x 64" are available for large lifting magnets.




Ventilated Dry-Type Transformer Coil. Both SG-200 and FHT Laminates are used in a wide variety of dry-type transformer





Grades FHT & SG-200

	UNIT	ASTM/UL Number	Grade FHT	Grade SG-200
General Information				
Part Number			1800	1906
Standard Color			Natural/Cream	Natural/Tan
Mechanical Properties				
NEMA Grade Li 1-1989			–	GPO-1
Tensile Strength	Psi	D638	10,500	12,500
Tensile Modulus	Psi X 10 ⁶	D638	–	1.7
Flexural Strength	Psi	D790	–	29,000
Compressive Strength	Psi	D695	14,000	36,000
Shear Strength	Psi	D732	–	11,100
IZOD Impact Strength (notched)	ft. lb./in.	D256	10	12
Water Absorption	% by wt.	D570	1.1	0.3
Specific Gravity	–	D792	1.6	1.7
Electrical Properties				
Electrical Strength – Perpendicular S/T in Air	V _{pm}	D149	450	500
Electrical Strength – Perpendicular S/T in Oil	V _{pm}	D149	570	625
Electrical Strength – Parallel S/S in Oil	kV	D149	60	50
Arc Resistance	Sec.	D495	139	120/180*
IEC Track Resistance (CTI) @ 3 mm thickness	V.	UL746A	>500	>500
UL High Voltage Track Rate	In./Min.	UL746A	0	0
Permittivity, 60 Hz	–	D150	6.4	4.6
Dissipation Factor, 60 Hz	–	D150	0.070	0.37
Permittivity, MHz	–	D150	4.2	3.7
Dissipation Factor, MHz	–	D150	0.033	0.013
Insulation Resistance	Ohm x 10 ¹²	D257	–	145
Flame Resistance Properties				
UL Subject 94	–	UL94	HB	HB
UL Hot Wire Ignition	Sec.	UL746A	0.028 in./49 0.058 in./102	0.028 in./35 0.058 in./39
UL High Amp Ignition	# Exposure	UL746A	200+	200+
Oxygen Index	%O ₂	D2863	21.8	21.8
Thermal Properties				
Coefficient of Thermal Expansion	In/In/°C x 10 ⁻⁵	D696	2	2
Thermal Conductivity	BTU/HR/Ft ² /In/°F	C177	1.7	1.7
UL Temperature Index				
– Electrical	°C	UL 746B	0.028 in./190 0.058 in./200	210
– Mechanical	°C	UL 746B	0.028 in./190 0.058 in./200	210
UL Recognition File Number	–	–	E81928	E81928



Röchling Glastic Composites
 4321 Glenridge Road
 Cleveland, OH 44121 USA
 Tel: 216-486-0100
 Fax: 216-486-1091
www.glastic.com

All of the information, suggestions, and recommendations pertaining to the properties and uses of the Röchling Glastic Composites products described herein are based upon tests and data believed to be accurate; however, the final determination regarding the suitability of any material described herein for the use contemplated, the manner of such use, and whether the use infringes any patents is the sole responsibility of the user. THERE IS NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Under no circumstances shall we be liable for incidental or consequential loss or damage.

Glastic® is a registered trademark of Röchling Glastic Composites. UL® is a registered trademark of Underwriters Laboratories, Inc.

©2012 Röchling Glastic Composites. All Rights Reserved. Printed in USA.

Typical average values for testing 0.063" thick material. Values will vary somewhat from thickness to thickness within a material grade.